

KEPITAL® F10-03H LOF

A stiffness-improved(high-viscosity) grade for general injection molding; low emission

- A stiffness-improved(high-viscosity) grade for general injection molding.
- A low-emission grade featuring thermal stability.
- Features greater stiffness compared to general POM copolymer.

Rheological properties

Moulding shrinkage range, parallel	2.2 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Tensile Modulus	2800 MPa	ISO 527-1/-2
Yield stress, 50mm/min	68 MPa	ISO 527-1/-2
Yield strain, 50mm/min	12 %	ISO 527-1/-2
Nominal strain at break	40 %	ISO 527-1/-2
Flexural Modulus	2600 MPa	ISO 178
Flexural Strength	90 MPa	ISO 178
Charpy notched impact strength, 23°C	7 kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	6.5 kJ/m²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	168 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120 E-6/K	ISO 11359-1/-2

Electrical properties

Surface resistivity	>1E16 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m³	ISO 1183

