

KEPITAL® TX-11H LOF

POM, friction and wear-resistance, medium-high viscosity grade for general injection molding, low emission

- A friction and wear-resistance (medium-high viscosity) grade for general injection molding.
- Suitable for uses requiring reduced wear noise and a good friction and wear resistance without sacrificing mechanical properties.
- A low emission grade featuring improved heat stability.

Product information

Part Marking Code	> POM <	ISO 11469
-------------------	---------	-----------

Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Tensile Modulus	2600 MPa	ISO 527-1/-2
Yield stress, 50mm/min	64 MPa	ISO 527-1/-2
Yield strain, 50mm/min	10 %	ISO 527-1/-2
Nominal strain at break	40 %	ISO 527-1/-2
Flexural Modulus	2550 MPa	ISO 178
Flexural Strength	86 MPa	ISO 178
Charpy notched impact strength, 23°C	9.5 kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	7 kJ/m²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	170 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	97 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120 E-6/K	ISO 11359-1/-2

Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1400 kg/m³	ISO 1183

