

KEPITAL® TE-22 LOF

POM, toughened, medium-viscosity grade, low emission

KEPITAL® TE-22 LOF is a toughened, medium-viscosity grade for general injection molding. Suitable for applications requiring high impact resistance, reduced impact noise and quality surface. A low-emission grade featuring improved heat stability.

Product information

Part Marking Code	> POM-HI <	ISO 11469
-------------------	------------	-----------

Rheological properties

Moulding shrinkage range, parallel	1.8 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Yield stress, 50mm/min	51 MPa	ISO 527-1/-2
Yield strain, 50mm/min	9.5 %	ISO 527-1/-2
Nominal strain at break	40 %	ISO 527-1/-2
Flexural Modulus	2000 MPa	ISO 178
Flexural Strength	68 MPa	ISO 178
Charpy notched impact strength, 23°C	10 kJ/m²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	76 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	HB class	UL 94
-------------------------------	----------	-------

Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E16 Ohm	IEC 62631-3-2

Other properties

Humidity absorption, 2mm	0.23 %	Sim. to ISO 62
Density	1370 kg/m³	ISO 1183

Other Approvals

Other Approvals	OEM	Specification
	GM	GMW22P-POM-C2P1

