

CELSTRAN® +PP-GF30-05CN05/10

PP with 30% ash content - impact modified copolymer, low emission

Material code according to ISO 1043-1: PP Polypropylene reinforced with 30 weight percent long glass fibers, Black. Impact modified copolymer, low emission. The fibers are chemically coupled to the polypropylene matrix. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage. Complex parts can be manufactured with high reproducibility by injection molding. Application field: Functional/structural parts for automotive

Typical mechanical properties

Tensile Modulus	6000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	95 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2.4 %	ISO 527-1/-2
Flexural Modulus	6000 MPa	ISO 178
Flexural Strength	150 MPa	ISO 178
Charpy impact strength, 23°C	60 kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	70 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	25 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	24 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	156 °C	ISO 75-1/-2
Temp. of deflection under load, 8 MPa	130 °C	ISO 75-1/-2

Other properties

Density	1110 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	90 - 100 °C
Drying Time, Dehumidified Dryer	2 h
Processing Moisture Content	0.2 %
Screw tangential speed	0.1 m/s
Max. mould temperature	30 - 70 °C
Back pressure	3 MPa
Injection speed	slow

Processing Texts

Pre-drying It is normally not necessary to dry CELSTRAN PP. However, should there be surface moisture (condensate) on the molding compound as a result of incorrect storage, drying is required.

Longer pre-drying times/storage The product can then be stored in standard conditions until processed.

