

OMNIPRO® CPP R GRC20 BK2000

Typical mechanical properties

Tensile Modulus	4900 MPa	ISO 527-1/-2
Stress at break, 5mm/min	60 MPa	ISO 527-1/-2
Strain at break, 5mm/min	4 %	ISO 527-1/-2
Flexural Modulus	5050 MPa	ISO 178
Charpy notched impact strength, 23°C	7 kJ/m ²	ISO 179/1eA

Other properties

Density	1040 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Max. mould temperature	30 - 60 °C
------------------------	------------

