

## POLIFOR C20 UV NEGRO 900 - PP

| Physical properties | Value | Unit              | Test Standard |
|---------------------|-------|-------------------|---------------|
| Density             | 900   | kg/m <sup>3</sup> | ISO 1183      |
| Melt flow rate, MFR | 20    | g/10min           | ISO 1133      |
| MFR temperature     | 230   | °C                | ISO 1133      |
| MFR load            | 2.16  | kg                | ISO 1133      |

| Mechanical properties             | Value | Unit              | Test Standard |
|-----------------------------------|-------|-------------------|---------------|
| Tensile stress at yield, 50mm/min | 27    | MPa               | ISO 527-2/1A  |
| Tensile strain at break, 50mm/min | >100  | %                 | ISO 527-2/1A  |
| Flexural modulus, 23°C            | 1200  | MPa               | ISO 178       |
| Izod impact notched, 23°C         | 6     | kJ/m <sup>2</sup> | ISO 180/1A    |

| Thermal properties                      | Value | Unit  | Test Standard |
|-----------------------------------------|-------|-------|---------------|
| DTUL at 1.8 MPa                         | 54    | °C    | ISO 75-1, -2  |
| Vicat softening temperature, 50°C/h 50N | 72    | °C    | ISO 306       |
| Flammability @1.6mm nom. thickn.        | HB    | class | UL 94         |

### Typical injection moulding processing conditions

| Pre Drying         | Value     | Unit | Test Standard |
|--------------------|-----------|------|---------------|
| Drying time        | 2 - 3     | h    | -             |
| Drying temperature | 80 - 100  | °C   | -             |
| Temperature        | Value     | Unit | Test Standard |
| Zone1 temperature  | 190 - 210 | °C   | -             |
| Zone2 temperature  | 210 - 230 | °C   | -             |
| Zone3 temperature  | 220 - 240 | °C   | -             |
| Melt temperature   | 230 - 250 | °C   | -             |
| Mold temperature   | 30 - 60   | °C   | -             |

