

POLIFOR® L30 GF/30 H X2

Polypropylene, homopolymer, 30% glass fiber reinforced, chemically coupled, Heat stabilized.

Rheological properties

Melt mass-flow rate	9 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile Modulus	6500 MPa	ISO 527-1/-2
Stress at break, 5mm/min	72 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2.8 %	ISO 527-1/-2
Flexural Modulus	6200 MPa	ISO 178
Flexural Strength	120 MPa	ISO 178
Charpy notched impact strength, 23°C	8 kJ/m²	ISO 179/1eA
Izod notched impact strength, 23°C	8.5 kJ/m²	ISO 180/1A

Thermal properties

Temp. of deflection under load, 1.8 MPa	144 °C	ISO 75-1/-2
---	--------	-------------

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94

Other properties

Density	1130 kg/m³	ISO 1183
---------	------------	----------

Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	50 - 80 °C

Other Approvals

Other Approvals

OEM	Specification
Stellantis - PSA Group	01994_17_00722
Renault	EP16a

