

TECNOPRENE® FKM24

PP homopolymer, 20% talc filled, 10% glass fibre reinforced, chemical bonded

Typical mechanical properties

Stress at break, 5mm/min	50 MPa	ISO 527-1/-2
Strain at break, 50mm/min	50 %	ISO 527-1/-2
Flexural Modulus	4500 MPa	ISO 178
Flexural Strength	80 MPa	ISO 178
Charpy notched impact strength, 23°C	5 kJ/m ²	ISO 179/1eA

Other properties

Density	1120 kg/m ³	ISO 1183
---------	------------------------	----------

