

TECNOPRENE® T60VB4 NERO900 - PP

Description

Polypropylene, 20% glass fiber reinforced, low flow, for blow molding technology

Physical properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183
Melt flow rate, MFR	1.6	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	4100	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	58	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	4.5	%	ISO 527-2/1A
Flexural modulus, 23°C	3700	MPa	ISO 178
Flexural strength, 23°C	92	MPa	ISO 178
Charpy notched impact strength, 23°C	12.5	kJ/m ²	ISO 179/1eA
Izod impact notched, 23°C	14	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	128	°C	ISO 75-1, -2
Flammability @1.6mm nom. thickn.	HB	class	UL 94

Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	200 - 220	°C	-
Zone2 temperature	220 - 240	°C	-
Zone3 temperature	240 - 260	°C	-
Nozzle temperature	240 - 260	°C	-

Other text information

Longer pre-drying times/storage

This product should be stored in a covered facility and kept away from moisture and heat.

Characteristics

Product Categories	Processing
Glass reinforced	Blow molding

