

SOPPRENE® 214G07862 GRIGIO - SBS

Physical properties	Value	Unit	Test Standard
Density	1040	kg/m³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile strain at break (TPE)	550	%	ISO 37
Tensile stress at break (TPE)	3.5	MPa	ISO 37
Shore A hardness, 3s	62	-	ISO 868
Tear strength	22	kN/m	ISO 34-1
Abrasion resistance	290	mm³	ISO 4649

Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	125 - 135	°C	-
Zone2 temperature	145 - 155	°C	-

