

SOPPRENE® 530000A50 NATURALE

Typical mechanical properties

Stress at 100% elongation	174 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	276 psi	ISO 527-1/-2 or ISO 37
Stress at break	377 psi	ISO 527-1/-2 or ISO 37
Elongation at break	650 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	51	ISO 48-4 / ISO 868
Tensile set	4 %	ISO 2285
Tear strength, normal	103 lb/in	ISO 34-1

Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

