

SOFPRENE® 540500A55 NEUTRO

Typical mechanical properties

Stress at 100% elongation	218 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	319 psi	ISO 527-1/-2 or ISO 37
Stress at break	566 psi	ISO 527-1/-2 or ISO 37
Elongation at break	750 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	55	ISO 48-4 / ISO 868
Tear strength, normal	143 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

