

SOFPRENE® 59999ZA80 NERO

Typical mechanical properties

Stress at 100% elongation	522 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	696 psi	ISO 527-1/-2 or ISO 37
Stress at break	856 psi	ISO 527-1/-2 or ISO 37
Elongation at break	460 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	83	ISO 48-4 / ISO 868
Tear strength, normal	217 lb/in	ISO 34-1

Other properties

Density	9 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

