

SOFPRENE® 540200A96 NEUTRO

Typical mechanical properties

Stress at 100% elongation	1000 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1120 psi	ISO 527-1/-2 or ISO 37
Stress at break	1670 psi	ISO 527-1/-2 or ISO 37
Elongation at break	600 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	96	ISO 48-4 / ISO 868
Tensile set	42 %	ISO 2285
Tear strength, parallel	326 lb/in	ISO 34-1

Other properties

Density	9 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

