

## SOFPRENE® SE600-80A - SBS

### Description

Semi-matte, translucent and rubber-like

| Physical properties | Value | Unit               | Test Standard |
|---------------------|-------|--------------------|---------------|
| Density             | 60.6  | lb/ft <sup>3</sup> | ISO 1183      |

| Mechanical properties (TPE) | Value | Unit            | Test Standard |
|-----------------------------|-------|-----------------|---------------|
| Shore A hardness-TPE, 3s    | 80    | -               | ISO 868       |
| Abrasion resistance         | 250   | mm <sup>3</sup> | ISO 4649      |

### Typical injection moulding processing conditions

| Temperature       | Value     | Unit |
|-------------------|-----------|------|
| Zone1 temperature | 212 - 230 | °F   |
| Zone2 temperature | 221 - 239 | °F   |
| Zone3 temperature | 248 - 266 | °F   |

