

LAPRENE® 830000815 NEUTRO

Typical mechanical properties

Stress at 100% elongation	11.4 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	11.4 MPa	ISO 527-1/-2 or ISO 37
Stress at break	14.3 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	618 %	ISO 527-1/-2 or ISO 37
Tear strength, normal	91 kN/m	ISO 34-1

Other properties

Density	900 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

Processing Texts

Pre-drying	Drying not necessary
Longer pre-drying times/storage	Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

