

**LAPRENE® 830000769/AB - SEBS**

Experimental Grade. Please contact your Celanese representative for further information.

| Physical properties | Value | Unit  | Test Standard |
|---------------------|-------|-------|---------------|
| Density             | 1160  | kg/m³ | ISO 1183      |

| Mechanical properties (TPE) | Value | Unit | Test Standard |
|-----------------------------|-------|------|---------------|
| Shore A hardness, 3s        | 67    | -    | ISO 868       |

**Typical injection moulding processing conditions**

| Temperature       | Value   | Unit | Test Standard |
|-------------------|---------|------|---------------|
| Zone1 temperature | 170     | °C   | -             |
| Zone2 temperature | 180     | °C   | -             |
| Zone3 temperature | 180     | °C   | -             |
| Zone4 temperature | 190     | °C   | -             |
| Mold temperature  | 20 - 40 | °C   | -             |

