

LAPRENE® 830000546/AB - SEBS

Experimental Grade. Please contact your Celanese representative for further information.

Physical properties	Value	Unit	Test Standard
Density	1140	kg/m³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Shore A hardness, 3s	75	-	ISO 868

Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	170	°C	-
Zone2 temperature	180	°C	-
Zone3 temperature	180	°C	-
Zone4 temperature	190	°C	-
Mold temperature	20 - 40	°C	-

