

LAPRENE® 830000850 NEUTRO

Typical mechanical properties

Shore A hardness, 3s	63	ISO 48-4 / ISO 868
----------------------	----	--------------------

Other properties

Density	897 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

Processing Texts

Pre-drying	Drying not necessary
------------	----------------------

Longer pre-drying times/storage	Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	---

