

LAPRENE® 830901546 NERO

Typical mechanical properties

Stress at 100% elongation	2.5 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	3.6 MPa	ISO 527-1/-2 or ISO 37
Stress at break	9.5 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	754 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	73	ISO 48-4 / ISO 868
Compression set at 70°C, 24h	45 %	ISO 815
Tensile set	9 %	ISO 2285
Tear strength, normal	36 kN/m	ISO 34-1

Other properties

Density	1160 kg/m³	ISO 1183
---------	------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

Processing Texts

Pre-drying	Drying not necessary
Longer pre-drying times/storage	Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

Other Approvals

Other Approvals	OEM	Specification	Additional Information
	Mercedes-Benz Group (Daimler)	DBL 5562	(5562.10); A 07/03
	VW Group	TL 526 22	

