

LAPRENE® 830901951 NERO - SEBS

Physical properties	Value	Unit	Test Standard
Density	56.2	lb/ft ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	174	psi	ISO 37
Tensile stress at 300%, perpendicular	348	psi	ISO 37
Tensile strain at break (TPE)	590	%	ISO 37
Tensile stress at break (TPE)	754	psi	ISO 37
Shore A hardness-TPE, 3s	45	-	ISO 868
Tear strength	120	lb/in	ISO 34-1

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	329 - 347	°F
Zone2 temperature	347 - 365	°F
Zone3 temperature	356 - 374	°F
Nozzle temperature	365 - 383	°F
Mold temperature	68 - 104	°F

Other text information
Pre-drying

Drying not necessary

Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

