

**LAPRENE® 83F000840 NEUTRO - SEBS**

| Physical properties | Value | Unit   | Test Standard |
|---------------------|-------|--------|---------------|
| Density             | 67.4  | lb/ft³ | ISO 1183      |

| Mechanical properties (TPE)                         | Value | Unit  | Test Standard |
|-----------------------------------------------------|-------|-------|---------------|
| Tensile stress at 100% strain                       | 43.5  | psi   | ISO 37        |
| Tensile stress at 300%, perpendicular               | 102   | psi   | ISO 37        |
| Compression Set under constant strain at 70 °C, 24h | 43    | %     | ISO 815       |
| Tensile strain at break (TPE)                       | 1230  | %     | ISO 37        |
| Tensile stress at break (TPE)                       | 537   | psi   | ISO 37        |
| Shore A hardness-TPE, 3s                            | 14    | -     | ISO 868       |
| Tear strength                                       | 74.3  | lb/in | ISO 34-1      |

**Typical injection moulding processing conditions**

| Temperature        | Value     | Unit |
|--------------------|-----------|------|
| Zone1 temperature  | 329 - 347 | °F   |
| Zone2 temperature  | 347 - 365 | °F   |
| Zone3 temperature  | 356 - 374 | °F   |
| Nozzle temperature | 365 - 383 | °F   |
| Mold temperature   | 68 - 104  | °F   |

**Other text information**
**Pre-drying**

Drying not necessary

**Longer pre-drying times/storage**

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

