

LAPRENE® 83K000786 NEUTRO

Typical mechanical properties

Stress at 100% elongation	0.6 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1.3 MPa	ISO 527-1/-2 or ISO 37
Stress at break	2.9 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	658 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	25	ISO 48-4 / ISO 868
Tear strength, normal	12 kN/m	ISO 34-1

Other properties

Density	925 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	30 - 50 °C
------------------------	------------

Processing Texts

Longer pre-drying times/storage	Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	---

