

LAPRENE® 83K000994/P1 NEUTRO

Typical mechanical properties

Stress at 100% elongation	1.1 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	2.2 MPa	ISO 527-1/-2 or ISO 37
Stress at break	3.2 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	482 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	44	ISO 48-4 / ISO 868
Tensile set	4 %	ISO 2285
Tear strength, normal	19 kN/m	ISO 34-1

Other properties

Density	912 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	30 - 50 °C
------------------------	------------

Processing Texts

Longer pre-drying times/storage	Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	---

