

---

**LAPRENE® NERO 830000765 - SEBS**

---

**Typical injection moulding processing conditions**

---

| Temperature        | Value     | Unit | Test Standard |
|--------------------|-----------|------|---------------|
| Zone1 temperature  | 165 - 175 | °C   | -             |
| Zone2 temperature  | 175 - 185 | °C   | -             |
| Zone3 temperature  | 180 - 190 | °C   | -             |
| Nozzle temperature | 185 - 195 | °C   | -             |
| Mold temperature   | 20 - 40   | °C   | -             |

---

**Other text information**

---

---

**Pre-drying**

---

Drying not necessary

---

**Longer pre-drying times/storage**

---

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

