

LAPRENE® L849-50A

Typical mechanical properties

Elongation at break	500 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	50	ISO 48-4 / ISO 868

Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--

