

# LAPRENE® L848-60A

## Typical mechanical properties

|                      |         |                        |
|----------------------|---------|------------------------|
| Stress at break      | 435 psi | ISO 527-1/-2 or ISO 37 |
| Elongation at break  | 500 %   | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 3s | 60      | ISO 48-4 / ISO 868     |

## Other properties

|         |           |          |
|---------|-----------|----------|
| Density | 10 lb/gal | ISO 1183 |
|---------|-----------|----------|

## Processing Texts

|                                 |                                                                                                                                      |
|---------------------------------|--------------------------------------------------------------------------------------------------------------------------------------|
| Longer pre-drying times/storage | The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat. |
|---------------------------------|--------------------------------------------------------------------------------------------------------------------------------------|

