

LAPRENE® NATURALE 8K3000A85 - SEBS

Physical properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	4.6	MPa	ISO 37
Tensile stress at 300% strain	8.2	MPa	ISO 37
Tensile strain at break (TPE)	590	%	ISO 37
Tensile stress at break (TPE)	17	MPa	ISO 37
Shore A hardness, 3s	85	-	ISO 868
Tear strength	67	kN/m	ISO 34-1

Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	175 - 185	°C	-
Zone2 temperature	185 - 195	°C	-
Zone3 temperature	195 - 205	°C	-
Nozzle temperature	185 - 195	°C	-
Extrusion Molding, Head Temperature	195 - 205	°C	Internal

Other text information

Pre-drying

2h@80C

Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

