

## LAPRENE® NERO 83E200A60/CB - SEBS

| Mechanical properties (TPE) | Value | Unit | Test Standard |
|-----------------------------|-------|------|---------------|
| Shore A hardness, 3s        | 62    | -    | ISO 868       |

### Typical injection moulding processing conditions

| Temperature                         | Value     | Unit | Test Standard |
|-------------------------------------|-----------|------|---------------|
| Zone1 temperature                   | 160 - 170 | °C   | -             |
| Zone2 temperature                   | 170 - 180 | °C   | -             |
| Zone3 temperature                   | 175 - 185 | °C   | -             |
| Nozzle temperature                  | 165 - 175 | °C   | -             |
| Extrusion Molding, Head Temperature | 180 - 190 | °C   | Internal      |

### Other text information

#### Pre-drying

Drying not necessary

#### Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

