

FORFLEX® 7RMP868/A NEUTRO

Typical mechanical properties

Stress at 100% elongation	9.8 MPa	ISO 527-1/-2 or ISO 37
Stress at break	13.8 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	106 %	ISO 527-1/-2 or ISO 37
Shore D hardness, 15s	61	ISO 48-4 / ISO 868

Other properties

Density	896 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

