

FORFLEX® 71Q001D56 NEUTRO

Typical mechanical properties

Stress at 100% elongation	13.7 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	14.2 MPa	ISO 527-1/-2 or ISO 37
Stress at break	13.9 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	667 %	ISO 527-1/-2 or ISO 37
Shore D hardness, 15s	60	ISO 48-4 / ISO 868
Tear strength, normal	128 kN/m	ISO 34-1

Other properties

Density	903 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

