

FORFLEX® 71G00IA75 NEUTRO

Typical mechanical properties

Stress at 100% elongation	2.6 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	3.3 MPa	ISO 527-1/-2 or ISO 37
Stress at break	12.9 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	1060 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	72	ISO 48-4 / ISO 868
Tear strength, normal	43 kN/m	ISO 34-1

Other properties

Density	870 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

