

FORFLEX® 71Q001D52 NEUTRO

Typical mechanical properties

Stress at 100% elongation	10.8 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	11.5 MPa	ISO 527-1/-2 or ISO 37
Stress at break	20.1 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	680 %	ISO 527-1/-2 or ISO 37
Shore D hardness, 15s	55	ISO 48-4 / ISO 868
Tear strength, normal	113 kN/m	ISO 34-1

Other properties

Density	900 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

