

FORFLEX® 71G001D62 NEUTRO

Rheological properties

Melt mass-flow rate	22 g/10min	ISO 1133
Melt mass-flow rate, Temperature	200 °C	
Melt mass-flow rate, Load	5 kg	

Typical mechanical properties

Yield stress, 50mm/min	26.6 MPa	ISO 527-1/-2
Yield strain, 50mm/min	13.6 %	ISO 527-1/-2
Stress at break, 50mm/min	26.6 MPa	ISO 527-1/-2
Strain at break, 50mm/min	1110 %	ISO 527-1/-2
Shore D hardness, 15s	64	ISO 48-4 / ISO 868
Tear strength, normal	117 kN/m	ISO 34-1

Other properties

Density	900 kg/m³	ISO 1183
---------	-----------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

