

# FORFLEX® TPT 033 BC BLUE

Styrene Butadiene Compound - Transparent  
Injection Molding Grade

## Rheological properties

Melt mass-flow rate	10 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	2.16 kg	

## Typical mechanical properties

Shore A hardness, 3s	92	ISO 48-4 / ISO 868
----------------------	----	--------------------

## Other properties

Density	930 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

## Injection

Max. mould temperature	30 - 50 °C
------------------------	------------

## Processing Texts

Pre-drying	Drying is not typically required
Longer pre-drying times/storage	The product should be stored in a covered facility away from moisture and heat.

