

FORPRENE® 6NM919A60 NERO - TPV

Physical properties	Value	Unit	Test Standard
Density	59.2	lb/ft³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100%, perpendicular	305	psi	ISO 37
Tensile stress at 300%, perpendicular	537	psi	ISO 37
Compression set, 70 °C, 22h, Type A	31	%	ISO 815
Tensile strain at break, perpendicular	417	%	ISO 37
Tensile stress at break, perpendicular	667	psi	ISO 37
Shore A hardness-TPE, 15s	62	-	ISO 868
Tear strength, Method Ba, perpendicular	114	lb/in	ISO 34-1
Tensile set (elastomers)	12	%	ASTM D412

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	347 - 365	°F
Zone2 temperature	365 - 383	°F
Zone3 temperature	374 - 392	°F
Nozzle temperature	383 - 401	°F
Mold temperature	68 - 104	°F

Other text information
Pre-drying

3h@80C

Longer pre-drying times/storage

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

Characteristics
Special Characteristics Auto spec approved

Other Approvals

OEM	Specification	Additional Information
BMW	AA-P 288	
Renault	UB09f	PMR2020
VW Group	VW50123	

