

SANTOPRENE® 121-70B230J

A soft, black thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is specially formulated to bond to sulfur or peroxide-cured thermoset EPDM rubber for corner molding, end caps and special fixation applications, and for COF enhancement. This grade of Santoprene® TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Specially formulated to replace thermoset EPDM rubber in automotive glass run channel corner molding applications
- Designed for shorter processing time compared to thermoset EPDM rubber
- Adheres to vulcanized EPDM rubber over wide range of temperatures
- Adheres to TPV over wide range of temperatures
- Enhanced COF properties
- Good UV resistance
- Low fogging
- Paint stain resistant

Typical mechanical properties

Stress at 100% elongation	377 psi	ISO 527-1/-2 or ISO 37
Stress at break	943 psi	ISO 527-1/-2 or ISO 37
Elongation at break	470 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	74	ISO 48-4 / ISO 868
Compression set at 70°C, 24h	44 %	ISO 815

Other properties

Density	479 lb/gal	ISO 1183
---------	------------	----------

Processing Texts

Processing Notes	Desiccant drying for 3 hours at 65°C (150°F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC.
------------------	---

