

SANTOPRENE® 121-70B265

Santoprene® 121-70B265 is a black thermoplastic vulcanizate (TPV) that combines low coefficient of friction with good bonding to TPV and EPDM rubber. This grade offers improved heat aging performance and excellent processability for injection molding of complex geometries with excellent surface aesthetics. It has low friction retention after heat aging without surface bleeding. It has been designed for corner molding and end cap of automotive extruded weather seals in TPV or in EDPM rubber.

Key Features

- Low friction injection molding grade
- Specially formulated to replace thermoset EPDM rubber in automotive glass run channel (GRC) corner molding applications
- Designed for shorter processing cycle time compared to thermoset EDPM rubber
- Adheres to vulcanized EPDM rubber and TPV
- Built-in low coefficient of friction properties
- Good flowability with excellent surface aspect

Typical mechanical properties

Low temperature brittleness	-85 °F	ISO 812
Shore A hardness, 15s	70	ISO 48-4 / ISO 868
Shore hardness change, after ageing	1.5	ISO 48-4 / ISO 868
Compression set at 70°C, 24h	36 %	ISO 815
Tear strength, normal	128 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Drying Temperature	176 °F	
Drying Time, Dehumidified Dryer	3 h	
Processing Moisture Content	0.08 %	
Max. regrind level	20 %	
Melt Temperature Optimum	419 °F	Internal
Max. mould temperature	104 - 140 °F	
Injection speed	fast	

Processing Texts

Processing Notes

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F). In order to obtain good bonding on an EPDM sponge profile, the injection speed should be fast (60 - 100mm/sec) and at a very high temperature in a warm mold. The injection pressure should be moderate and the holding pressure kept low in order to prevent profile deformation. The profile should be moderate and the holding pressure kept low in order to prevent profile deformation. The profile should be perfectly positioned in the mold and maintained without deformation to

Printed: 2023-09-25



SANTOPRENE® 121-70B265

ensure maximum surface interaction with the melt. Cooling time should be longer than a typical TPV in order to initiate recrystallization at the contact interface. Santoprene® TPV is incompatible with acetal and PVC.

Other Approvals

Other Approvals

OEM	Specification
GM	GMW15825P-TPV, Type 5

