

Hytrel[®] 60LW THERMOPLASTIC POLYESTER ELASTOMER

Hytrel® 60LW is a Polyester Elastomer Concentrate Developed for Enhancing Abrasion and Wear Resistance

Product information Resin Identification Part Marking Code	TPC-EP-SD >TPC-EP-SD<		ISO 1043 ISO 11469
Rheological properties Melt volume-flow rate Temperature Load	6 220 2.16	•	ISO 1133
Thermal properties Melting temperature, 10°C/min	210	°C	ISO 11357-1/-3
Flammability FMVSS Class Burning rate, Thickness 1 mm	B <80	mm/min	ISO 3795 (FMVSS 302) ISO 3795 (FMVSS 302)
Other properties Density of melt	910	kg/m³	Internal
Characteristics			
Additives Release agen	t		
Chemical Media Resistance			
 Aceids Acetic Acid (5% by mass), 23°C Citric Acid solution (10% by mass), 23°C Lactic Acid (10% by mass), 23°C Hydrochloric Acid (36% by mass), 23°C Nitric Acid (40% by mass), 23°C Sulfuric Acid (38% by mass), 23°C Sulfuric Acid (5% by mass), 23°C Chromic Acid solution (40% by mass), 23°C 			
Bases ✓ Sodium Hydroxide solution (35% by mass), 23 ✓ Sodium Hydroxide solution (1% by mass), 23 ✓			

- Sodium Hydroxide solution (1% by mass), 23°C
- Ammonium Hydroxide solution (10% by mass), 23°C

Printed: 2023-09-22



Page: 1 of 3





Hytrel[®] 60LW THERMOPLASTIC POLYESTER ELASTOMER

Alcohols

- Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

X Acetone, 23°C

Ethers

X Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- X SAE 80/90 hypoid-gear oil, 130 °C
- ✓ Insulating Oil, 23°C

Standard Fuels

- X ISO 1817 Liquid 1 E5, 60°C
- X ISO 1817 Liquid 2 M15E4, 60°C
- X ISO 1817 Liquid 3 M3E7, 60 °C
- 🗙 ISO 1817 Liquid 4 M15, 60°C
- Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ➤ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- X Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✓ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ★ Hydrogen peroxide, 23°C
- X DOT No. 4 Brake fluid, 130°C
- ★ Ethylene Glycol (50% by mass) in water, 108°C
- 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- X Water, 90°C

Printed: 2023-09-22



Page: 2 of 3





Hytrel[®] 60LW THERMOPLASTIC POLYESTER ELASTOMER

✓ Phenol solution (5% by mass), 23°C

Symbols used:

possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

★ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).



