

Hytrel[®] 4053FG NC010 THERMOPLASTIC POLYESTER ELASTOMER

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants. Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytrel® 4053FG is a low modulus high performance thermoplastic elastomer developed for applications in contact with food. It is suitable for extrusion and injection molding processes.

FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from our representative.

Typical applications:

Hose and tubing, hose jackets, wire and cable jackets, film and sheeting, belting and seals.

Product information

Resin Identification	TPC-ET		ISO 1043
Fait Marking Code	>IFG-EI<		150 1 1409
Rheological properties			
Melt volume-flow rate	5	cm ³ /10min	ISO 1133
Melt mass-flow rate	5.3	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Melt mass-flow rate, Temperature	190	°Č	
Melt mass-flow rate, Load	2.16	kg	
Moulding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.4	%	ISO 294-4, 2577
Typical mechanical properties			
Tensile Modulus	56	MPa	ISO 527-1/-2
Stress at 5% strain	2.4	MPa	ISO 527-1/-2
Stress at 10% strain	4.4	MPa	ISO 527-1/-2
Stress at 50% strain	7.3	MPa	ISO 527-1/-2
Stress at break	26	MPa	ISO 527-1/-2
Printed: 2023-09-22			







Hytrel[®] 4053FG NC010 THERMOPLASTIC POLYESTER ELASTOMER

Strain at break Tensile creep modulus, 1h Tensile creep modulus, 1000h Charpy impact strength, 23°C Charpy impact strength, -30°C Charpy notched impact strength, 23°C Charpy notched impact strength, -30°C Charpy notched impact strength, -40°C Tensile notched impact strength, 23°C Poisson's ratio Shore D hardness, 15s Tear strength, parallel	>300 50 40 N N N 230 0.5 38 110	% MPa kJ/m ² kJ/m ² kJ/m ² kJ/m ² kJ/m ² kJ/m ²	ISO 527-1/-2 ISO 899-1 ISO 899-1 ISO 179/1eU ISO 179/1eU ISO 179/1eA ISO 179/1eA ISO 179/1eA ISO 8256/1 ISO 48-4 / ISO 868 ISO 34-1
Thermal properties			
Melting temperature, 10°C/min Glass transition temperature, 10°C/min Temp. of deflection under load, 0.45 MPa Coeff. of linear therm. expansion, parallel Coeff. of linear therm. expansion, normal Eff. thermal diffusivity	150 -50 50 220 220 5.44E-8	°C °C °C E-6/K E-6/K m ² /s	ISO 11357-1/-3 ISO 11357-1/-3 ISO 75-1/-2 ISO 11359-1/-2 ISO 11359-1/-2 ISO 11359-1/-2 Internal
Flammability			
Burning Behav. at 1.5mm nom. thickn. Thickness tested UL recognition Oxygen index FMVSS Class	HB 1.5 yes 20 SE	class mm %	UL 94 UL 94 UL 94 ISO 4589-1/-2 ISO 3795 (FMVSS 302)
Electrical properties			
Relative permittivity, 100Hz Relative permittivity, 1MHz Dissipation factor, 100Hz Dissipation factor, 1MHz Volume resistivity Surface resistivity Electric strength Comparative tracking index	5.2 4.7 110 525 7E10 2E14 18 600	E-4 E-4 Ohm.m Ohm kV/mm	IEC 62631-2-1 IEC 62631-2-1 IEC 62631-2-1 IEC 62631-2-1 IEC 62631-3-1 IEC 62631-3-2 IEC 60243-1 IEC 60112
Other properties			
Humidity absorption, 2mm Water absorption, 2mm Density Density of melt	0.2 0.7 1160 1020	% % kg/m ³ kg/m ³	Sim. to ISO 62 Sim. to ISO 62 ISO 1183 Internal

Printed: 2023-09-22







Hytrel[®] 4053FG NC010

Injection

Drying Recommended	yes	
Drying Temperature	80	°C
Drying Time, Dehumidified Dryer	2 - 3	h
Processing Moisture Content	≤0.08	%
Melt Temperature Optimum	180	°C
Min. melt temperature	170	°C
Max. melt temperature	190	°C
Mold Temperature Optimum	40	°C
Min. mould temperature	30	°C
Max. mould temperature	40	°C
Extrusion		
Drying Temperature	70 - 90	°C
Drying Time, Dehumidified Dryer	2 - 3	h
Processing Moisture Content	≤0.06	%
Melt Temperature Optimum	170	°C
Melt Temperature Range	165 - 180	°C

Internal

Additional information

Injection molding

Snake Flow Test, mm

Inject press 62MPa, 1mm	80
Inject press 62MPa, 2.5mm	330
Inject press 83MPa(12,000psi), 1mm	95
Inject press 83MPa(12,000psi), 2.5mm	430

Chemical Media Resistance

Other

✓ Water, 90°C

Symbols used:

✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

★ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Printed: 2023-09-22



