

Hytre[®] 8238HS NCB010 (PRELIMINARY)

THERMOPLASTIC POLYESTER ELASTOMER

Common features of Hytre[®] thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants. Hytre[®] thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytre[®] thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations.

For disposal, local regulations have to be observed.

Hytre[®] thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

Hytre[®] 8238HS NCB010 is the highest modulus grade, with nominal hardness of 82D. It contains non-discoloring stabilizer and a cube blended heat stabilizer. It can be processed by many conventional thermoplastic processing techniques like injection molding and extrusion.

Typical applications:

Cubing, wire and cable, gears, sprockets, electrical connectors and oil field parts.

Product information

| | | |
|----------------------|----------|-----------|
| Resin Identification | TPC-ET | ISO 1043 |
| Part Marking Code | >TPC-ET< | ISO 11469 |

Rheological properties

| | | |
|------------------------------|-------|-----------------|
| Moulding shrinkage, parallel | 1.4 % | ISO 294-4, 2577 |
| Moulding shrinkage, normal | 1.4 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|---------------------------------------|-----------------------|--------------------|
| Tensile Modulus | 1000 MPa | ISO 527-1/-2 |
| Yield stress | 38 MPa | ISO 527-1/-2 |
| Yield strain | 19 % | ISO 527-1/-2 |
| Stress at 10% strain | 36 MPa | ISO 527-1/-2 |
| Stress at break | 49 MPa | ISO 527-1/-2 |
| Nominal strain at break | 250 % | ISO 527-1/-2 |
| Strain at break | 290 % | ISO 527-1/-2 |
| Flexural Modulus | 1000 MPa | ISO 178 |
| Charpy notched impact strength, 23°C | 5.5 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -40°C | 3.5 kJ/m ² | ISO 179/1eA |
| Poisson's ratio | 0.45 | |
| Shore D hardness, 15s | 70 | ISO 48-4 / ISO 868 |
| Shore D hardness, max | 71 | ISO 868 |

Printed: 2023-09-22

Page: 1 of 2



Hytre[®] 8238HS NCB010 (PRELIMINARY)

THERMOPLASTIC POLYESTER ELASTOMER

Thermal properties

| | | |
|--|-------|----------------|
| Glass transition temperature, 10°C/min | 45 °C | ISO 11357-1/-3 |
|--|-------|----------------|

Injection

| | | |
|---------------------------------|---------|----------|
| Drying Recommended | yes | |
| Drying Temperature | 110 °C | |
| Drying Time, Dehumidified Dryer | 2 - 3 h | |
| Processing Moisture Content | ≤0.08 % | |
| Melt Temperature Optimum | 250 °C | Internal |
| Min. melt temperature | 245 °C | |
| Max. melt temperature | 260 °C | |
| Mold Temperature Optimum | 45 °C | |
| Min. mould temperature | 45 °C | |
| Max. mould temperature | 55 °C | |
| Hold pressure range | ≥70 MPa | |

Extrusion

| | |
|---------------------------------|--------------|
| Drying Temperature | 100 - 120 °C |
| Drying Time, Dehumidified Dryer | 2 - 3 h |
| Processing Moisture Content | ≤0.06 % |
| Melt Temperature Range | 235 - 250 °C |

