

Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

Rheological properties

Melt volume-flow rate	7 cm ³ /10min	ISO 1133
Melt mass-flow rate	7.8 g/10min	ISO 1133
Temperature	220 °C	
Load	2.16 kg	
Melt mass-flow rate, Temperature	220 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage, parallel	1.4 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.4 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	180 MPa	ISO 527-1/-2
Yield stress	15 MPa	ISO 527-1/-2
Yield strain	40 %	ISO 527-1/-2
Stress at 5% strain	6.9 MPa	ISO 527-1/-2
Stress at 10% strain	11 MPa	ISO 527-1/-2
Stress at 50% strain	14.5 MPa	ISO 527-1/-2
Stress at 100% strain	16 MPa	ISO 527-1/-2
Stress at break	40 MPa	ISO 527-1/-2
Nominal strain at break	600 %	ISO 527-1/-2
Strain at break	>300 %	ISO 527-1/-2
Flexural Modulus	190 MPa	ISO 178
Tensile creep modulus, 1h	170 MPa	ISO 899-1
Tensile creep modulus, 1000h	133 MPa	ISO 899-1
Charpy impact strength, 23°C	N kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	N kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	145 ^[P] kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	145 kJ/m ²	ISO 179/1eA
Tensile notched impact strength, 23°C	320 kJ/m ²	ISO 8256/1
Puncture - maximum force, 23°C	2400 N	ISO 6603-2
Puncture - maximum force, -30°C	3700 N	ISO 6603-2
Puncture energy, 23°C	27 J	ISO 6603-2
Puncture energy, -30°C	43 J	ISO 6603-2
Izod notched impact strength, 23°C	N kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	N kJ/m ²	ISO 180/1A
Poisson's ratio	0.48	
Brittleness temperature	-98 °C	ISO 974
Shore D hardness, 15s	51	ISO 48-4 / ISO 868
Shore D hardness, max	55	ISO 868
Tear strength, parallel	137 kN/m	ISO 34-1
Tear strength, normal	134 kN/m	ISO 34-1
Abrasion resistance	120 mm ³	ISO 4649

[P]: Partial Break



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

Thermal properties

Melting temperature, 10°C/min	201 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-25 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	45 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	70 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	75 °C	ISO 306
Vicat softening temperature, 50°C/h 10N	180 °C	ISO 306
Coeff. of linear therm. expansion, parallel, -40-23°C	160 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	180 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	174 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	180 E-6/K	ISO 11359-1/-2
Thermal conductivity of melt	0.16 W/(m K)	Internal
Eff. thermal diffusivity	7E-8 m²/s	Internal
Spec. heat capacity of melt	2110 J/(kg K)	Internal
RTI, electrical, 0.75mm	85 °C	UL 746B
RTI, electrical, 1.5mm	85 °C	UL 746B
RTI, electrical, 3mm	85 °C	UL 746B
RTI, impact, 0.75mm	50 °C	UL 746B
RTI, impact, 1.5mm	85 °C	UL 746B
RTI, impact, 3mm	85 °C	UL 746B
RTI, strength, 0.75mm	50 °C	UL 746B
RTI, strength, 1.5mm	75 °C	UL 746B
RTI, strength, 3mm	80 °C	UL 746B

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Thickness tested	1.5 mm	UL 94
UL recognition	yes	UL 94
Burning Behav. at thickness h	HB class	UL 94
Thickness tested	3 mm	UL 94
UL recognition	yes	UL 94
Oxygen index	20 %	ISO 4589-1/-2
Glow Wire Flammability Index, 2mm	700 ^[DS] °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 2mm	675 ^[DS] °C	IEC 60695-2-13
Glow Wire Temperature, No Flame, 2mm	650 ^[DS] °C	IEC 60335-1
FMVSS Class	SE	ISO 3795 (FMVSS 302)

[DS]: Derived from similar grade



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

Electrical properties

Relative permittivity, 100Hz	4.8	IEC 62631-2-1
Relative permittivity, 1MHz	4.4	IEC 62631-2-1
Dissipation factor, 100Hz	90 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	375 E-4	IEC 62631-2-1
Volume resistivity	4E11 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1
Comparative tracking index	600	IEC 60112

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.6 %	Sim. to ISO 62
Water absorption, Immersion 24h	0.6 %	Sim. to ISO 62
Density	1190 kg/m³	ISO 1183
Density of melt	1030 kg/m³	Internal

Film Properties

WVTR, 23°C/85%r.h.	300 g/(m²*d)	DIS 15106-1/-2
Oxygen transmission rate, 23°C/85%r.h.	6000 cm³/(m²*d*bar)	DIS 15105-1/-2
Thickness of specimen	0.025 mm	

VDA Properties

Light stability delta I	3	DIN 53236
Light stability delta a	-2	DIN 53236
Light stability delta b	13	DIN 53236
Light stability delta E	14	DIN 53236
Emission of organic compounds	8.5 µgC/g	VDA 277
Odour	5 class	VDA 270
Fogging, G-value (condensate)	0.1 mg	ISO 6452

Injection

Drying Recommended	yes	
Drying Temperature	100 °C	
Drying Time, Dehumidified Dryer	2 - 3 h	
Processing Moisture Content	≤0.08 %	
Melt Temperature Optimum	230 °C	Internal
Min. melt temperature	220 °C	
Max. melt temperature	250 °C	
Mold Temperature Optimum	45 °C	
Min. mould temperature	45 °C	
Max. mould temperature	55 °C	



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

Extrusion

Drying Temperature	90 - 110 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Processing Moisture Content	≤0.06 %
Melt Temperature Optimum	225 °C
Melt Temperature Range	220 - 235 °C

Characteristics


Additives	Biobased
-----------	----------



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Viscosity-shear rate



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Shearstress-shear rate



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Dynamic Tensile modulus-temperature



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Stress-strain



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Secant modulus-strain



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Stress-strain (isochronous) 23°C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Creep modulus-time 23°C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Stress-strain (isochronous) 40°C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Creep modulus-time 40°C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Stress-strain (isochronous) 80°C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Creep modulus-time 80°C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER


Specific volume-temperature (pvT)



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

Stress-Strain (Flexible Materials)



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23 °C
- ✓ Citric Acid solution (10% by mass), 23 °C
- ✓ Lactic Acid (10% by mass), 23 °C
- ✗ Hydrochloric Acid (36% by mass), 23 °C
- ✗ Nitric Acid (40% by mass), 23 °C
- ✗ Sulfuric Acid (38% by mass), 23 °C
- ✓ Sulfuric Acid (5% by mass), 23 °C
- ✗ Chromic Acid solution (40% by mass), 23 °C

Bases

- ✓ Sodium Hydroxide solution (35% by mass), 23 °C
- ✓ Sodium Hydroxide solution (1% by mass), 23 °C
- ✓ Ammonium Hydroxide solution (10% by mass), 23 °C

Alcohols

- ✓ Isopropyl alcohol, 23 °C
- ✓ Methanol, 23 °C
- ✓ Ethanol, 23 °C

Hydrocarbons

- ✓ n-Hexane, 23 °C
- ✓ Toluene, 23 °C
- ✓ iso-Octane, 23 °C

Ketones

- ✗ Acetone, 23 °C

Ethers

- ✗ Diethyl ether, 23 °C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23 °C
- ✗ SAE 10W40 multigrade motor oil, 130 °C
- ✗ SAE 80/90 hypoid-gear oil, 130 °C
- ✓ Insulating Oil, 23 °C
- ✗ Motor oil OS206 304 Ref.Eng.Oil, ISP, 135 °C
- ✗ Automatic hypoid-gear oil Shell Donax TX, 135 °C
- ✗ Hydraulic oil Pentosin CHF 202, 125 °C

Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5, 60 °C
- ✗ ISO 1817 Liquid 2 - M15E4, 60 °C
- ✗ ISO 1817 Liquid 3 - M3E7, 60 °C
- ✗ ISO 1817 Liquid 4 - M15, 60 °C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23 °C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23 °C



Hytrel® ECO 5556B

THERMOPLASTIC POLYESTER ELASTOMER

- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✓ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✓ Water, 90°C
- ✓ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

