

RITEFLEX® RKX-150 - TPC

Experimental Grade. Please contact your Celanese representative for further information.

Physical properties	Value	Unit	Test Standard
Melt flow rate, MFR	30	g/10min	ISO 1133
MFR temperature	220	°C	ISO 1133
MFR load	2.16	kg	ISO 1133
Water absorption, 23°C-sat	0.5	%	ISO 62

Mechanical properties	Value	Unit	Test Standard
Flexural modulus, 23°C	82	MPa	ISO 178
Flexural stress at 3.5% strain	3	MPa	ISO 178
Charpy notched impact strength, 23°C	28	kJ/m ²	ISO 179/1eA

Characteristics
Product Categories

Unfilled

