

GUR® 5523

Melt processable UHMW-PE pellet grade Version: 1.0; Date: 01-17-2020
 Melt processable UHMW-PE pellet grade; screw extrusion grade
 Some of the listed data have been determined from the virgin powder material.

Product information

Average molecular weight	6.7E6 g/mol	Margolies' equation
--------------------------	-------------	---------------------

Rheological properties

Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	21.6 kg	
Viscosity number	3000 cm³/g	ISO 307, 1157, 1628
Intrinsic viscosity	2500	ISO 307, 1157, 1628

Typical mechanical properties

Tensile Modulus	740 MPa	ISO 527-1/-2
Yield stress, 50mm/min	20 MPa	ISO 527-1/-2
Yield strain, 50mm/min	13 %	ISO 527-1/-2
Stress at 50% strain	19 MPa	ISO 527-1/-2
Stress at break, 50mm/min	38 MPa	ISO 527-1/-2
Nominal strain at break	410 %	ISO 527-1/-2
Elongational stress, 150/10	0.24 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	160 kJ/m²	ISO 21304-2

Tribological properties

Relative Wear (based on GUR 4120=100), sandslurry method	110	Internal
---	-----	----------

Thermal properties

Vicat softening temperature, 50°C/h, 50N	80 °C	ISO 306
--	-------	---------

Other properties

Density	930 kg/m³	ISO 1183
Bulk density	500 kg/m³	ISO 60

