

GUR® 4019-7

Very coarse particle UHMW-PE powder grade for porous application
 Very coarse particle UHMW-PE powder grade for porous application

Product information

Average molecular weight	5.5E6 g/mol	Margolies' equation
Average particle size, D50	450 µm	laser scattering

Rheological properties

Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	21.6 kg	
Viscosity number	2500 cm³/g	ISO 307, 1157, 1628
Intrinsic viscosity	2250	ISO 307, 1157, 1628

Typical mechanical properties

Yield stress, 50mm/min	23 MPa	ISO 527-1/-2
Yield strain, 50mm/min	12 %	ISO 527-1/-2
Stress at 50% strain	21 MPa	ISO 527-1/-2
Stress at break, 50mm/min	33 MPa	ISO 527-1/-2
Nominal strain at break	360 %	ISO 527-1/-2
Elongational stress, 150/10	0.12 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	160 kJ/m²	ISO 21304-2

Tribological properties

Relative Wear (based on GUR 4120=100), sandslurry method	130	Internal
---	-----	----------

Thermal properties

Vicat softening temperature, 50°C/h, 50N	80 °C	ISO 306
--	-------	---------

Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E12 Ohm	IEC 62631-3-2

Other properties

Density	940 kg/m³	ISO 1183
Bulk density	470 kg/m³	ISO 60

Printed: 2023-09-22

