

GUR® 4550

UHMW-PE powder grade
 UHMW-PE powder grade

Product information

Average molecular weight	8.7E6 g/mol	Margolies' equation
Average particle size, D50	120 µm	laser scattering

Rheological properties

Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	21.6 kg	
Viscosity number	3700 cm³/g	ISO 307, 1157, 1628
Intrinsic viscosity	3000	ISO 307, 1157, 1628

Typical mechanical properties

Tensile Modulus	600 MPa	ISO 527-1/-2
Yield stress, 50mm/min	19 MPa	ISO 527-1/-2
Yield strain, 50mm/min	16 %	ISO 527-1/-2
Stress at 50% strain	19 MPa	ISO 527-1/-2
Stress at break, 50mm/min	43 MPa	ISO 527-1/-2
Nominal strain at break	420 %	ISO 527-1/-2
Elongational stress, 150/10	0.5 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	180 kJ/m²	ISO 21304-2
Shore D hardness, 15s	60	ISO 48-4 / ISO 868

Tribological properties

Relative Wear (based on GUR 4120=100), sandslurry method	85	Internal
---	----	----------

Thermal properties

Vicat softening temperature, 50°C/h, 50N	80 °C	ISO 306
--	-------	---------

Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E12 Ohm	IEC 62631-3-2

Other properties

Density	930 kg/m³	ISO 1183
Bulk density	470 kg/m³	ISO 60




GUR[®] 4550

Characteristics

Food contact

FDA 21 CFR

Stress-strain



GUR[®] 4550

Secant modulus-strain

