

Accutech ABS831G40L

Acrylonitrile Butadiene Styrene

LyondellBasell Industries

Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.35	1.35 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 Kg)	0.50 g/10 min	0.50 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	841000 psi	5800 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	11300 psi	78.0 MPa	
Break	11300 psi	78.0 MPa	
Tensile Elongation			ASTM D638
Yield	2.0 %	2.0 %	
Break	3.0 %	3.0 %	
Flexural Modulus	1.52E+6 psi	10500 MPa	ASTM D790
Flexural Strength	16000 psi	110 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.2 ft·lb/in	64 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	105	105	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	212 °F	100 °C	
264 Psi (1.8 Mpa), Unannealed	198 °F	92.0 °C	

Notes

These are typical property values not to be construed as specification limits.

