

Accucomp ABS881L

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Appearance	• Clear/Transparent		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.07	1.07 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 Kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	290000 psi	2000 MPa	ASTM D638
Tensile Strength (Yield)	6240 psi	43.0 MPa	ASTM D638
Tensile Elongation (Break)	20 %	20 %	ASTM D638
Flexural Modulus	290000 psi	2000 MPa	ASTM D790
Flexural Strength	8700 psi	60.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	2.4 ft·lb/in	130 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	189 °F	87.0 °C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

