

Accucomp ABS892BL

Acrylonitrile Butadiene Styrene

LyondellBasell Industries

Engineering Plastics

General			
Features	• High Heat Resistance		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 Kg)	0.80 g/10 min	0.80 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	247000 psi	1700 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	7540 psi	52.0 MPa	
Break	5510 psi	38.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	20 %	20 %	
Flexural Modulus	377000 psi	2600 MPa	ASTM D790
Flexural Strength	10400 psi	72.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	6.9 ft·lb/in	370 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	104	104	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	208 °F	98.0 °C	
264 Psi (1.8 Mpa), Unannealed	180 °F	82.0 °C	

Notes

These are typical property values not to be construed as specification limits.

