



Lucent Abs ABS-305LG

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

Product Description

Low Gloss, General Purpose Acrylonitrile Butadiene Styrene

Add "R" for Added Release
Add "U" for UV Stabilizer

General

- | | | |
|----------|-------------------|-------------|
| Features | • General Purpose | • Low Gloss |
| Uses | • General Purpose | |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	6100 psi	42.1 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	320000 psi	2210 MPa	ASTM D790
Flexural Strength	10800 psi	74.5 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	3.0 ft·lb/in	160 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed	190 °F	87.8 °C	

Notes

These are typical property values not to be construed as specification limits.

